

Technical Data Sheet BrazeTec D 4900.1

Standard

ISO 17672
(DIN EN 1044)
DIN EN 1045

Ag 449 (Brazing Alloy)
(AG 502)
FH 10 (Flux)

Nominal composition [wt.-%]

Permitted impurities max. [wt.-%]
Max. impurities [wt.-%]

Ag 49; Cu 16; Zn 23; Mn 7.5; Ni 4.5
Al 0.001; Bi 0.030; Cd 0.010; P 0.008; Pb 0.025; Si 0.05
0.30

Technical data

Melting range of brazing alloy	approx. 680 - 705 °C
Working temperature	approx. 690 °C
Density of brazing alloy	approx. 8.9 g/cm ³
Density of brazing paste	approx. 2.7 g/cm ³ (20 °C)
Metal content	approx. 65 wt.-%
Grain size of brazing alloy powder	< 106 µm
Viscosity	1100 - 1300 dPa s (Haake Viscotester 02; Sp. 2, 20 ±2 °C)
Residues	corrosive, soluble in water
Shear strength acc. DIN EN 12797	250 - 300 MPa
Operating temperature of joint	max. 200 °C (without loss of strength)
Cleaning agent	BrazeTec Cleaning Agent P
Shelf life	Can / bucket: min. 6 months Cartridge: min. 3 months in the original closed container. Storage temperature +5 to +30 °C. Stir cans and buckets well before use.

Packaging

Standard 0.075; 1; 3; 5; 10 kg

Applications

BrazeTec D 4900.1 is a dosable brazing paste for use with brazing machines. It contains flux and a low melting free flowing silver brazing alloy.

The brazing alloy is suitable for brazing of cemented carbides and materials which are difficult to wet, such as tungsten, molybdenum, tantalum and chromium.

The dosable brazing paste BrazeTec D 4900.1 is suitable for all common brazing methods, like torch brazing, furnace brazing and induction brazing.

Typical applications are found e.g. in the tool industry.

Further comments: Paste residues are corrosive and have therefore to be removed carefully.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at <http://www.saxonia-tm.de/en/TechnicalMaterials/agbs/>.