

Technical data sheet BrazeTec P 1002.4

Standard

ISO 17672 (US-Standard ANSI/AWS A5.8) (DIN EN 1044)	Ni 620 (BNi-2) (NI 102)
---	-------------------------------

Nominal composition [wt.-%]

Permitted impurities max. [wt.-%]	Ni Rem.; Cr 7.0; Si 4.5; B 3.1; Fe 3.0 Al 0.05; Co 0.10; S 0.02; Se 0.005; Ti 0.05; Zr 0.05 C 0.06; P 0.02
Max. impurities [wt.-%]	0.50

Technical data

Melting range of brazing alloy	approx. 970 - 1000 °C
Optimum brazing temperature	approx. 1050 °C
Density of brazing alloy	approx. 8,0 g/cm ³
Density of brazing paste	approx. 3,9 g/cm ³ (20 °C)
Metal content	approx. 90 wt.-%
Grain size of brazing alloy powder	< 63 µm
Viscosity	28 - 36 Pa s (Cone-Plate; 150 µm; D= 50/s; 20 °C)
Flash point of solvent	approx. 105 °C
Evaporation temperature of binder	approx. 360 - 400 °C at 1 bar
Cleaning agent	BrazeTec Cleaning Agent P
Shelf life	6 months in the original closed container storage temperature +5 to +30 °C. stir well before use.

Packaging

Standard	1; 3; 5; 10; 25 kg
----------	--------------------

Applications

BrazeTec P 1002.4 is a suspension consisting of a brazing alloy powder, filler metal and a solvent based binder system which is used to apply thin brazing alloy layers on work piece surfaces. The suspension can be applied by conventional screen printing techniques.

The nickel based brazing alloy can be used for coating through brazing nickel and nickel alloys, cobalt and cobalt alloys, any steels and stainless steel, and in some cases for special metals and their alloys.

The shape of the applied layer will stay stable during brazing process. The brazing alloy does not flow over the surface.

The brazing process has to be carried out in vacuum or protective atmosphere. Nitrogen containing atmospheres are not suitable for this brazing alloy.

To evaporate the solvent a drying process at temperatures between 70 °C and 120 °C has to be carried out. A drying chamber/furnace with an exhaust system should be used to avoid explosive vapor-air-mixtures. The brazing process should include a holding time at 400 °C to ensure a residue free burn-out of the binder.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at <http://www.saxonia-tm.de/en/TechnicalMaterials/agbs/>.